

IMPERTOP FAST 2K

RAYSTON
products

Hand-applied flexible polyaspartic topcoat for waterproofing membranes

DESCRIPTION

Impertop Fast 2k is a flexible 2-component, slow reactivity polyaspartic, that, unlike usual polyurea systems, it can be mixed and manually applied due to its moderated reaction speed while retaining a fast-curing profile once applied. It is delivered in colourless or pigmented versions. Good chemical resistance. Designed as protective aliphatic topcoat for waterproofing membranes.

APPLICATIONS

UV protection of waterproofing membranes (Polyurea Rayston, Impermax 2k, Impermax) of Rayston products, either cold and hot-applied. Resistant to motor and pedestrian traffic. Also applied as protective topcoat in water-containing tanks (sewage, chlorinated, brine, etc.).

ADVANTAGES

Suitable for aliphatic protective topcoat for aromatic PU, polyurea waterproofing membranes.

- Fast curing.
- Good adhesion properties.
- High hardness and resistance, achieved with a single application.
- Excellent gloss and colour retention.
- Aliphatic polyisocyanate basis. No discolouration.
- Good weathering resistance.
- Suitable as an aliphatic topcoat for waterproofing membranes.
- Several tests prove that these coatings inhibit corrosion in metal surfaces.

TECHNICAL DATA

INFORMATION ON THE PRODUCT BEFORE APPLICATION

	Component A	Component B
Chemical description	Polyamines solution	Solvent less aliphatic polyisocyanate
Physical state	Liquid	Liquid
Packaging	Metal container	Metal container
	Colourless	Colourless:
	2.95 kg	1.05 kg
	11 kg	4 kg
	Pigmented	Pigmented
	3.85 kg	1.15 kg
	11.6 kg	3.4 kg
Non-volatile content	Colourless: 73%	100%
	Pigmented: 68%	
Flash point	35°C	>100°C
Colour	See product list for available colours	Colourless
Density	Colourless: 1.0 g/cm ³ (25°C) Pigmented: 1.05 g/cm ³ (25°C)	1.15 g/cm ³ (25°C)
Viscosity	Colourless: 25 mPa.s (25°C) Pigmented: 35 mPa.s (25°C)	450 mPa.s (25°C)
A/B mixing ratio	Colourless A=100, B=36 by weight A=100, B=31.5 by volume Pigmented A=100, B=29 by weight A=100, B=27.5 by volume	
Mixture properties	Density: 1.04 g/cm ³ Viscosity: 105 mPa.s (clear), 115 mPa.s (pigmented) Non-volatile content: 80% (clear), 75% (pigmented)	

Colour	Colourless if not pigmented. Available colours in the product list.	
Pot life	Conditions 22°C 40%hr	Pot life(min) 30
Storage	Keep at 10°C and 30°C.	
Use before	12 months after manufacture date.	

INFORMATION ON THE FINAL PRODUCT

Final state	Solid polyaspartic/polyurethane coating
Colour	Colourless. Other colours available under request.
Hardness (Shore)	55D
Density	1.07 g/cm ³ (colourless) 1.15 g/cm ³ (pigmented)
Mechanical properties	Elongation at break: 150% Tensile strength: 22 MPa (EN-ISO 527-3)
UV resistance	Colour stable under sunlight
Chemical resistance	Surface contact, 24 h room temperature (5=best, 0=worst)

Chemical	Result
Water	5
Isopropyl alcohol	3
Xylene	1
Ammonia 3%	5
Sodium Hydroxide 50%	5
Acetic acid 10%	5
Acetic acid 20%	4
Sulphuric acid 50%	3
Hydrochloric acid 10%	5
Hydrochloric acid 20%	3
Bleach	5
Sodium hypochlorite 15%	5
Hydrogen peroxide 10%	5
Hydrogen peroxide 33%	0
Petrol	2
Diesel	4

SUPPORT REQUIREMENTS

Support must have enough mechanical strength, free from any vapour or water pressure. Support must also be clean, dry and free from poorly adhesive areas. Recommended support temperature: 10°C to 25°C.

ENVIRONMENTAL CONDITIONS

Recommended air temperature: 10°C to 30°C

Recommended humidity: 40% to 80%

SUPPORT PREPARATION

On recently applied sprayed waterproofing membrane: For better adhesion apply topcoat shortly (30 min) after application of the membrane.

Older membranes: gentle sanding and cleaning with rayston solvent and use of PU primer is advised.

MIXING

Open component A container. Stir using a low-speed stirrer preventing an excessive air bubbling, until dispersion of fillers. Pour component B in it and stir gently for 2 minutes. Transfer the mixture to a bigger container and check there is no unmixed product left.

APPLICATION

Apply by roller. Airless equipment is not recommended due to safety reasons.



KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies
43890 - l'Hospitalet de l'Infant - Spain
Tel: +34 977 822 245 - Fax: +34 977 823 977
www.kryptonchemical.com - rayston@kryptonchemical.com

Latest update:

11/02/2026

Page:

1/2

IMPERTOP FAST 2K

RAYSTON
products



Hand-applied flexible polyaspartic topcoat for waterproofing membranes

Reaction rate increases with the size of the mixtures; therefore, it is advised not to mix more amount of product than that can be easily applied in a 15-minute period. Otherwise, application could be difficult, or the final appearance could be affected.

RECOMMENDED QUANTITIES

Impertop Fast 2k can be applied in a wide thickness range. It is recommended to apply 200 to 500 microns when dry. (200 to 600 g/m² wet film).

CURING TIME

Curing time depends strongly on the local conditions. Curing speed will increase with temperature and humidity. The following table gives approximate values for 200 g/m² applications. Thicker coats will give longer curing times.

Conditions	Touch cure (h)	Total cure(h)
22°C, 40% rh	2	3
8°C, 50% rh	3	5

RECOATING

Only one coat is usually needed.

RETURN TO SERVICE

Under most conditions a light traffic is permitted about 2 hours after it is dry to touch. A normal use is recommended only the following day.

TOOL CLEANING

Component A and B can be cleaned with solvent Rayston. Cured product cannot be dissolved, unless special stripping products are used. Due to its fast-curing rate, A+B mixture stain must be cleaned as soon as possible. A daily water scrubbing is allowed. Solvents may seriously damage the surface.

FAQ

Problem	Answer
It can be thinned?	Not usually needed. If desired, some solvent can be added, but keep in mind that this will result in a longer drying time, and colour could be affected. Solvents must be always polyurethane grade. They must be absolutely free from alcohols or water, or any substance that can affect the crosslinking reaction. Recommended solvents are xylene or methoxypropyl acetate (PMA).
Is spreading of quartz sand allowed?	Yes. The pot life gives enough time for the application of antislip additives (Quartz sand, bauxite, etc) between two coats. Please refer to Krypton Chemical advice for further information on the application details.
Can it be pigmented?	Please refer to Krypton Chemical advice for colour options and procedures

⚠

MAINTENANCE

A daily water scrubbing is allowed. Solvents may seriously damage the surface.

SAFETY

Impertop Fast 2k contains isocyanates and flammable solvents. Always follow the instructions provided in the material safety data sheet and take the precautions described there.

As a rule, suitable ventilation must be ensured, and any skin contact avoided.

This product is intended to be used only for the uses and in the way here described. Sprayed application methods are not recommended due to health/safety reasons. This product is to be used only by industrial or professional users. It is not suitable for DIY-type uses.

ENVIRONMENTAL PRECAUTIONS

Empty containers must be handled taking the same precautions as if they were full. Containers must be considered as hazardous waste, to be transferred to an authorized waste manager.

OTHER INFORMATION

The information contained in this DATA SHEET, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend to study deeply all information provided before proceeding to the use or application of any of our products and strongly advise to conduct tests "on-site" in order to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise.

The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This data sheet supersedes previous versions.



KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies
43890 - l'Hospitalet de l'Infant - Spain
Tel: +34 977 822 245 - Fax: +34 977 823 977
www.kryptonchemical.com - rayston@kryptonchemical.com

Latest update:

11/02/2026

Page:

2/2